

TRILITE® KH-70

Gaussian Strong Acid Cation Exchange Resin

Rev 3. Feb 2023

TRILITE® is KH-70 Strong Acid Cation Exchange Resin. Because of its excellent ion removal capacity, high purity water can be produced economically. TRILITE® KH-70 is a premium grade resin not only for industrial but also domestic softening. It features decreased initial coloring matters and impurity release of cation resins by post-treatment and reduced bad odor through process control. TRILITE® KH-70 has outstanding mechanical and chemical stability, leading to low crush rate even after long-term use. TRILITE® KH-70 is supplied in Na⁺ form.

Physical and Chemical Properties

Matrix	Polystyrene+DVB, Gel	Functional Group	Sulfonic acid
Ionic Form	Na ⁺	Total Capacity(eq/ℓ)	1.90 ↑
Shipping Density(g/ℓ)	800	Moisture Retention(%)	45~50
Particle Density	1.25	Uniformity Coefficient	1.6 ↓
Particle Size(μm)	300~1,200	Swelling Rate(Na ⁺ →H ⁺ , %)	8~9
Whole Beads(%)	95 ↑		

Recommended Operating Conditions

Operating Temp(°C)	120 ↓	pH Range	0~14
Bed Depth(mm)	800	Service Flow Rate(m/h)	5~50

Regeneration

Regenerant	NaCl	Concentration(%)	6~10
Level(g/ℓ)	50~200	Flow Rate(m/h)	4~20
Rinse Requirement(BV)	4~10		

Applications

TRILITE® KH-70 is a product certified by NSF for use in drinking water.

All information contained in brochure is not absolute rather than relative one, created under the controlled environment by Samyang Corporation. Therefore, Samyang Corporation has no legal responsibility with respect to any and all information provided in brochure.

Samyang's TRILITE Ion exchange resins are produced based on the ISO 9001, ISO 14001 certification.

Samyang Corporation, 31 Jong-ro 33-gil, Jongno-gu, Seoul, Korea Tel: (02)740-7732~7, Fax: (02)740-7140



<http://samyangtrilite.com>